

DESCRIPTION

Welding wires and rods to be used when very high seawater corrosion resistance is needed. Applications in the construction of ships, offshore, cryogenic plants, railway and in the automotive industry.

AWS A5.10/A5.10M

ER 5183, R5183

EN ISO 18273

S Al 5183 / AlMg_{4,5}Mn_{0,7}(A)

MATERIALS TO BE WELDED

Al Mg 4,5 Mn / Al Mg 5 / Al Mg 2 Mn 0,8 / Al Zn Mg 1 / Al Zn Mg Cu 0,5 /

Al Mg Si 0,5 / Al Mg Si 1 / G-Al Mg 10 / G-Al Mg 5 / G-Al Mg 3 Si /

G-Al Mg 5 Si

SHIELDING GASES FOR GMAW/GTAW

l₁, l₂, l₃

MINIMAL VALUES OF THE MECHANICAL PROPERTIES (welded metal)

Tensile strenght R_m: 275 N/mm²

Yeld strenght R_{p 0,2}: 130 N/mm²

Elongation L=5d: 18 %

AVAILABLE SIZES*

MIG: 5-6-7 Kg D300 or K300/KS300 spools

Diameter of the wire

0,8 mm - 0,9 mm - 1,0 mm - 1,2 mm - 1,6 mm - 2,0 mm - 2,4 mm

TIG carton box of 10 Kg (x 1000 mm length)

Diameter of the rods

1,6 mm-2,0 mm-2,4 mm-3,2 mm-4,0 mm-5,0 mm

MINI-MIG: 0,5 Kg D100 spools / 2 Kg D200 spools

Diameter of the wire

0,8 mm - 0,9 mm - 1,0 mm - 1,2 mm - 1,6 mm

* More diameters and packaging upon request

CHEMICAL COMPOSITION

in% (m/m)^(a)

Al remainder

Si 0,40

Fe 0,40

Cu 0,10

Mn 0,50 - 1,0

Mg 4,3 - 5,2

Cr 0,05 - 0,25

Zn 0,25

Ti 0,15

Be 0,0003

others each
< 0,05

others total
0,15

(a) Single values shown in the table are maximum values, unless otherwise noted.